

This Page Is Inserted by IFW Operations
and is not a part of the Official Record

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images may include (but are not limited to):

- BLACK BORDERS
- TEXT CUT OFF AT TOP, BOTTOM OR SIDES
- FADED TEXT
- ILLEGIBLE TEXT
- SKEWED/SLANTED IMAGES
- COLORED PHOTOS
- BLACK OR VERY BLACK AND WHITE DARK PHOTOS
- GRAY SCALE DOCUMENTS

IMAGES ARE BEST AVAILABLE COPY.

**As rescanning documents *will not* correct images,
please do not report the images to the
Image Problems Mailbox.**



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁵ : B01J 23/89, 23/46, 21/18 C07C 29/00	A1	(11) International Publication Number: WO 93/14867 (43) International Publication Date: 5 August 1993 (05.08.93)
(21) International Application Number: PCT/EP93/00194 (22) International Filing Date: 28 January 1993 (28.01.93) (30) Priority data: TO92A000080 31 January 1992 (31.01.92) IT (71) Applicants: MONTECATINI TECNOLOGIE S.R.L. [IT/IT]; NOVAMONT S.P.A. [IT/IT]; Foro Buonaparte, 31, I-20121 Milano (IT). (72) Inventors: GUBITOSA, Giuseppe ; Via Dellavecchia, 5, I-28100 Novara (IT). CASALE, Bruno ; Strada Rondini, 14, I-28062 Cameri (IT). (74) Agents: RAMBELLI, Paolo et al.; Jacobacci-Casetta & Perani S.p.A., Via Alfieri, 17, I-10121 Torino (IT).		(81) Designated States: AU, BR, CA, CZ, FI, HU, JP, KR, NO, NZ, PL, RU, SK, UA, European patent (AT, BE, CH, DE, DK, ES, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE). Published <i>With international search report.</i> <i>Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i>
(54) Title: A HYDROGENATION CATALYST, AND A METHOD FOR ITS PREPARATION AND USE, IN PARTICULAR FOR HYDROGENATION AND/OR HYDROGENOLYSIS OF CARBOHYDRATES AND POLYHYDRIC ALCOHOLS (57) Abstract A metallic catalyst composition on an inert support, suitable in particular for hydrogenolysis reactions of higher polyhydric alcohols, characterized in that it comprises the following relative to 100 parts of the catalyst: a) 0.5 to 5 weight % ruthenium; b) 1 to 10 weight % of a metal selected from the group consisting of palladium, platinum and rhodium; and c) 0.5 to 2.5 weight % copper, in which the copper content is lower than the content of the metal b). The catalyst is used in particular for producing lower polyhydric alcohols such as ethanediol, propylene glycol, butanediol and glycerol, by means of hydrogenolysis reaction of higher polyhydric alcohols.		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	FR	France	MR	Mauritania
AU	Australia	GA	Gabon	MW	Malawi
BB	Barbados	GB	United Kingdom	NL	Netherlands
BE	Belgium	GN	Guinea	NO	Norway
BF	Burkina Faso	GR	Greece	NZ	New Zealand
BG	Bulgaria	HU	Hungary	PL	Poland
BJ	Benin	IE	Ireland	PT	Portugal
BR	Brazil	IT	Italy	RO	Romania
CA	Canada	JP	Japan	RU	Russian Federation
CF	Central African Republic	KP	Democratic People's Republic of Korea	SD	Sudan
CG	Congo	KR	Republic of Korea	SE	Sweden
CH	Switzerland	KZ	Kazakhstan	SK	Slovak Republic
CI	Côte d'Ivoire	LI	Liechtenstein	SN	Senegal
CM	Cameroon	LK	Sri Lanka	SU	Soviet Union
CS	Czechoslovakia	LU	Luxembourg	TD	Chad
CZ	Czech Republic	MC	Monaco	TG	Togo
DE	Germany	MG	Madagascar	UA	Ukraine
DK	Denmark	ML	Mali	US	United States of America
ES	Spain	MN	Mongolia	VN	Viet Nam
FI	Finland				

A hydrogenation catalyst, and a method for its preparation and use, in particular for hydrogenation and/or hydrogenolysis of carbohydrates and polyhydric alcohols

The present invention relates to methods for hydrogenation of carbohydrates and hydrogenolysis of higher polyhydric alcohols, and to a new hydrogenation catalyst which is useful in particular for producing lower polyhydric alcohols from renewable materials, such as in particular carbohydrates and higher polyhydric alcohols.

In the present description, the term "higher polyhydric alcohols" means products such as sorbitol, mannitol and xylitol derived from catalytic hydrogenation of carbohydrates (and in particular of glucose, fructose and their mixtures).

The term "lower polyhydric alcohols" means polyalcohols having a maximum of 6 carbon atoms and a maximum of 3 hydroxyl groups, in particular ethanediol, propylene glycol, butanediol and glycerol.

The invention also relates to a method for preparing the new catalyst.

U.S. 2,868,847 describes a method for catalytic hydrogenation of mono- and disaccharides for producing polyhydroxyl alcohols, in particular sorbitol, and proposes replacing the known platinum and palladium-based catalysts used for this method, by a ruthenium

catalyst or by a metallic catalyst based on ruthenium and platinum or palladium.

U.S. 4,476,331 describes a method for producing lower polyhydric alcohols comprising a first stage of hydrogenation of carbohydrates with production of higher polyhydric alcohols and a second stage in which the higher polyhydric alcohols are subjected to hydrogenolysis in the presence of a ruthenium-based catalyst which is pre-sulphurised or is sulphurised in use by addition of sulphurised compounds to the reactive medium. Sulphurisation of the ruthenium-based catalyst is necessary in order to limit the hydrogenolysis reaction which would otherwise lead to the formation of highly hydrogenated compounds (hydrocarbons, and in particular methane).

The main object of the present invention is to provide a method for hydrogenolysis of higher polyhydric alcohols which has a high selectivity towards the production of lower polyhydric alcohols, thus keeping to a minimum the formation of gaseous hydrocarbons which constitute an undesirable product.

For this purpose an object of the present invention is a new metallic catalyst on an inert support, characterised in that it comprises the following relative to the (anhydrous) weight of the catalyst:

- a) 0.5 to 5 weight % ruthenium;
 - b) 1 to 10 weight % of a metal selected from the group consisting of palladium, platinum and rhodium; and
 - c) 0.5 to 2.5 weight % copper,
- and in which the copper content is lower than the content of the metal b).

In particular use of palladium with a weight ratio of between 2 and 4 Pd/Cu is preferred in the catalyst.

A second object of the invention is a method for producing lower polyhydric alcohols and their mixtures by means of hydrogenolysis under pressure of higher polyhydric alcohols, in the presence of a metal catalyst on activated carbon consisting of the catalyst previously described.

The catalyst support preferably comprises powdered or granulated activated carbon. For continuous fixed bed hydrogenation and hydrogenolysis methods, a granulated activated carbon is preferably used, which has:

- a specific surface area of 600 to 1000 m²/g, preferably from 800 to 1000 m²/g (B.E.T. method);
- a total pore volume of 0.5 to 1.2 cm³/g and preferably 0.6 to 0.7 cm³/gr (combined nitrogen-mercury method);
- an apparent specific weight (bulk density) of 0.3 to 0.8 gr/cm³ and preferably 0.45 to 0.55 g/cm³;

- an actual specific weight of 1.9 to 2.3 g/cm³;
- a total volume of micropores having a radius smaller than 75 Å of 0.4 to 0.55 cm³/g; and
- an ash content of 2 to 5 weight %

By granulated activated carbon is meant a carbon which has a minimum granule size of at least 0.5 mm and a particle size of between 0.5 and 5.7 mm (3 - 32 mesh; Tiller series). The optimum particle size is selected on the basis of the process parameters, according to known criteria.

Granulated activated carbon of the above-described type is available commercially from amongst the activated carbons produced by ACQUE NYMCO under references GH12132 and CA12132.

In the hydrogenolysis reaction of higher polyhydric alcohols, the catalyst preferably has:

- a') 1 to 3 weight % ruthenium;
- b') 2 to 6 weight % of the metal selected from amongst palladium, platinum and rhodium, and preferably palladium; and
- c') 0.5 to 2% weight copper.

The weight ratio between copper and the metal from group b) is preferably between 0.2 and 0.5.

The catalyst according to the invention is prepared by means of a method which comprises the following operations.

An aqueous solution is prepared which contains a compound of ruthenium and a second metal selected from amongst platinum, palladium and rhodium, with a concentration of the metals such that after the support has been impregnated, a concentration within the limits previously indicated of metal in the catalyst is obtained. The precursor used for the active elements is a ruthenium compound soluble in water, and preferably ruthenium trichloride, and a soluble compound of palladium, platinum or rhodium and preferably their chlorinated compounds such as H_2PdCl_4 and Na_2PdCl_4 .

The aqueous solution containing the metals is then put into contact with an aqueous solution of the activated carbon, followed by adjustment of the pH by addition of an alkaline agent until a value of 4.5 to 8 is obtained; in the preferred embodiment the activated carbon is in the form previously described; when the aqueous solution of catalytic compounds has been put into contact with the suspension of the support, the pH of the suspension thus obtained is preferably allowed to stabilise at a value of approximately 1, and an aqueous solution of an alkaline compound is then

added in a quantity such that the pH of the resulting suspension is between 4.5 and 5; after approximately an hour the pH is regulated by means of further addition of the alkaline agent to a value no higher than 8 and preferably to between 6 and 8.

The suspension is then heated to a temperature of between 70° and 100°C, and is preferably maintained at this temperature for a length of time which is generally between 30 minutes and 2 hours, and is sufficient to give rise to depositing of compounds of the metals on the activated carbon, which is then separated from the suspension; during this impregnation process the two metals are deposited in the support substantially in the form of highly dispersed oxides in close contact with one another, in concentrations of 0.5 to 5 weight % ruthenium and 0.1 to 10 weight % palladium, platinum or rhodium.

The separated solid thus obtained is then suspended in an alkaline solution, and the suspension thus obtained is processed with gaseous hydrogen at a temperature of between 60° and 100°C for 1 - 4 hours and preferably for 3 hours; during this hydrogenation process the oxides, and in particular palladium oxide, are reduced to the metallic state.

An aqueous solution of copper is then added to the

suspension at a temperature preferably lower than 50°C. An aqueous solution of copper formate is preferably used, in which the copper concentration is such that a concentration of 0.5 to 2.5 weight % copper is obtained on the support. The copper is easily reduced on the palladium and is deposited in the form of a metal in close contact with the two metals previously deposited on the activated carbon.

The alkaline agent used for adjustment of the pH may be a hydroxide, a carbonate or a bicarbonate of the alkaline elements, and preferably sodium carbonate.

The method for hydrogenolysis of higher polyhydric alcohols according to the invention is preferably carried out continuously on a fixed bed reactor. The reaction temperature is generally between 200° and 300°C and preferably 220° - 270°C, the spatial velocity of the fluid is between 0.3 and 4h⁻¹ and preferably between 0.6 and 2.50 h⁻¹, and the reaction pressure is between 5 and 20 MPa and preferably between 7.5 and 15 MPa. The continuous reactor is preferably supplied with a reaction promoter selected from amongst alkaline and alkaline-earth hydroxides, and preferably sodium hydroxide or calcium hydroxide, or basic reaction salts; the molar ratio between higher polyhydric alcohols and the promoter supplied is between 2 and 30.

According to the hydrogenolysis method, the supply comprises a higher polyhydric alcohol or mixture of polyhydric alcohols, supplied to the hydrogenation reactor preferably in an aqueous solution having a concentration of 20 to 40 weight %.

The higher polyhydric alcohol or mixture of higher polyhydric alcohols is advantageously obtained in a first stage of hydrogenation of carbohydrates carried out with a low basic pH, preferably of between 7.5 and 8, at a reaction temperature of between 120° and 150°C. This first stage is also preferably carried out in an aqueous solution, in the presence of a basic promoter such as those previously described, in a quantity sufficient to maintain the pH in the aforementioned field. The reaction is preferably carried out in a fixed bed, using a catalyst comprising 0.5 to 5 weight % ruthenium supported on granulated activated carbon having the above-described characteristics. The preparation of this catalyst is similar to that described for the catalyst comprising ruthenium, palladium and copper, the only difference being that the palladium and copper compounds are not used.

In this first stage the carbohydrate may comprise monosaccharides or disaccharides. The preferred supply however comprises an aqueous solution of glucose, which

is converted with virtually maximum theoretical yield into sorbitol. Sorbitol constitutes the preferred supply substrate for the hydrogenolysis process which, owing to use of the catalyst according to the invention, enables ethanediol, 1.2-propylene glycol, butanediol, and smaller amounts of glycerol, lactic acid and monovalent alcohols, as well as products such as erythritol and pentanediols to be obtained with a high level of selectiveness.

The catalyst thus obtained has the characteristics of porosity, specific surface area and specific weight particular to the original activated carbon.

In this method the catalyst according to the invention enables the formation of undesirable gaseous hydrocarbons to be reduced without needing to use sulphurated compounds either in the catalyst or in the reactive medium.

Example 1: preparation of the catalyst.

For preparation of the catalyst according to the present invention, an activated carbon of vegetable origin and preferably derived from coconut (palm) having the following features is used:

specific surface area: $800 \text{ m}^2/\text{g}$ (B.E.T.);

actual specific weight: $2.1 \text{ g}/\text{cm}^3$;

total pore volume: $0.64 \text{ cm}^3/\text{g}$;

10

volume of micropores ($R > 75 \text{ \AA}$): $0.5 \text{ cm}^3/\text{g}$;

apparent specific weight (bulk density) 0.48 g/cm^3 ;

ash content: 3 weight %;

particle size:

10 - 18 mesh: (Tiller series $2 \div 1 \text{ mm}$): 20 - 30 weight %

18 - 35 mesh: (Tiller series $1 \div 0.5 \text{ mm}$): 80 - 70 weight %.

A quantity of 300 g granulated activated carbon of this type having 6% humidity is suspended in 2 litres of distilled water, washed preliminarily then filtered and suspended in a litre of distilled water, and continues to be subjected to mechanical agitation. After approximately 30 minutes the pH of the suspension is 10.

1 litre of solution of RuCl_3 and Na_2PdCl_4 containing 6 g Ru and 15 g Pd is added slowly and continuously for a period of approximately 1 hour to this suspension. The pH of the suspension when this addition is completed is 0.92; it is then increased to 4.8 by adding a 1M solution of sodium carbonate, and after approximately 60 minutes the pH is increased to 6 by means of a further addition of sodium carbonate. The suspension is then heated to a temperature of 90°C and is maintained at this temperature for approximately 1 hour.

The solid is separated from the suspension by means of filtering and washing. It is then re-suspended in 2 litres of 0.1 M solution of sodium carbonate. An argon flow is bubbled through the suspension, which is contained in a three-necked flask and is being gently agitated mechanically, until the air is entirely removed. The argon flow is then replaced by a hydrogen flow and the suspension is heated to a temperature of 80°C. The suspension is maintained at 80°C for approximately 2 hours. The hydrogen flow is then replaced by an argon flow, and the suspension is cooled to 50°C. 500 cm³ of aqueous solution of copper formate containing 4.5 g Cu is added slowly and continuously for a period of approximately 30 minutes to this suspension, and agitation of the suspension is continued for approximately 2 hours. The catalyst is filtered and washed until there are no chlorides left in the washing waters. The wet catalyst which has a ruthenium, palladium and copper base is kept moist in a sealed container, and has the following concentrations in weight of the activated metals: 2% Ru, 5% Pd and 1.5% Cu.

Examples 2 - 4: production of lower polyhydric alcohols.

The catalyst prepared according to example 1 is used for the conversion of sorbitol to lower polyhydric alcohols in various experimental conditions and using

the following general method.

250 cm³ of aqueous solution containing 80 g sorbitol, 5.5 g calcium hydroxide and a variable amount of catalyst is introduced into an autoclave which has a volume of 500 cm³, and is provided with a manometer, a mechanical, magnetically driven agitator with four inclined blades, wash-plates, and a heating system. The autoclave is closed and the air it contains is eliminated by washing with inert gas. The inert gas is then replaced by hydrogen, and the autoclave is loaded under pressure to 13 MPa using hydrogen at ambient temperature. The heating and the agitation at 660 rpm are then begun. The required temperature is reached after approximately 1 hour, and is maintained for 2 hours. The pressure is increased to 15 -19 MPa by the effect of heating, and then drops to 12 - 16.5 MPa owing to reaction. After the two-hour period the autoclave is cooled down by supplying water to the cooling jacket until ambient temperature is reached, and before the autoclave is de-pressurised a gas sample is collected for analysis. The reaction fluid is then discharged and is separated from the catalyst by filtration.

The gas sample collected is analysed by gas chromatography in order to ascertain the presence of any hydrocarbons (methane, ethane, ethylene etc) and

carbon dioxide. The reaction fluid is analysed by means of high pressure liquid chromatography (HPLC).

The fluid product contains mainly 1.2-propylene glycol, ethanediol, glycerol, lactic acid and a smaller amount of butanediol and monovalent acids. The gas contains small amounts of methane and traces of carbon dioxide.

The results of examples 2 - 4 for three different molar ratios of sorbitol/ ruthenium in the reactive medium are given in tables 1 and 2 hereinafter, relative respectively to the operative conditions and distribution of the reaction products.

TABLE 1

Example	Temp. (°C)	Molar ratio sorbitol/ ruthenium	Conversion (% sorbitol.)
2	250	446	75
3	250	222	87.6
4	250	111	97.5

TABLE 2

Distribution of products (% of carbon atoms)

Example	methane	monovalent alcohols	ethanediol	1-2 propylene glycol	butanediol	glycerol	lactic acid	others
2	4.0	7.5	18.3	33.2	4.8	11.4	15.3	5.5
3	4.8	8.8	17.2	34.4	5	10.7	13.0	6.1
4	9.2	6.3	14.4	36.0	6.3	7.1	10.3	10.4

The results in tables 1 and 2 show that a decrease of the sorbitol/ ruthenium ratio in the reactive medium lead to an increase in the conversion, however to the detriment of selectiveness as far as the gaseous products (methane) are concerned.

Examples 5 - 8

The catalyst obtained according to example 1 is used in the conversion of sorbitol according to the methods in examples 2 to 4, at various reaction temperatures. The results of these tests are given in tables 3 and 4 hereinafter.

TABLE 3

Example	Temp. (°C)	Molar ratio sorbitol/ ruthenium	Conversion (% sorbitol)
5	275	222	96.3
6	250	222	87.6
7	225	222	75.4
8	200	222	79.4

TABLE 4

Distribution of products (% of carbon atoms)

Example	methane	monovalent alcohols	ethanediol	1-2 propylene glycol	butanediol	glycerol	lactic acid	others
5	10.4	9.7	15.4	30.6	3.7	4.4	11	14.8
6	4.8	8.8	17.2	34.4	5.0	10.7	13	6.1
7	3.2	7.0	17.5	35.4	4.4	13.5	14.4	4.6
8	0.2	3.0	17.4	40.5	5.4	11.6	10.6	11.3

Examples 9 - 11

The catalyst prepared according to example 1 is used for the conversion of sorbitol at various reaction temperatures, according to the method in examples 2 ÷

4. The operative conditions and results of the tests are given in tables 5 and 6 hereinafter.

TABLE 5

Example	Temp. (°C)	Molar ratio sorbitol/ ruthenium	Conversion (% sorbitol)
9	250	111	97.5
10	225	111	87.5
11	200	111	80.0

TABLE 6

Distribution of products (% of carbon atoms)

Example	methane	monovalent alcohols	ethanediol	1-2 propylene glycol	butanediol	glycerol	lactic acid	others
9	9.2	6.3	14.4	36.0	6.3	7.1	10.3	10.4
10	5.1	1.7	15.8	34.1	4.1	14.6	10.9	13.7
11	2.34	6.8	15.5	33.3	3.6	15.4	12.2	10.9

Examples 12 - 14

The catalyst (100 cm^3) prepared according to example 1 is loaded in a tubular fixed bed reactor which has a descending and equally distributed flow, provided with a gas - fluid separator at the reactor outlet, a reaction fluid supply tank and a hydrogen gas tank. The reactor has a diameter of 20.5 mm (the height of the catalytic bed is 30 cm) and is equipped with a coaxial thermocouple which has 3 temperature measurement areas, disposed at 2.5, 15 and 28 cm below the topmost level of the catalytic bed. Above the catalytic bed there is a layer of inert material 7.5 cm deep, which ensures that the reagents are satisfactorily mixed before coming into contact with the catalytic bed itself.

The reactor is closed and is connected to a system for supply of the reagents and discharge of the products. The system is pressurised with nitrogen in order to check its airtightness. The reactor is then supplied at the test pressure with 2 flows: a mixed hydrogen - water flow obtained by injecting water into the hydrogen current, and a second flow of deionised water at ambient temperature. Before the two flows reach the catalytic bed they are thoroughly mixed through the layer of inert material. The reactor is then heated until it reaches the test temperature in approximately 2 hours. In these conditions the water flow is replaced

by a flow of aqueous sorbitol solution containing sodium hydroxide. After approximately 8 hours the temperature and spatial velocity (LHSV) are in a steady state. After this stabilisation period collection of the chemical reaction products at two-hourly intervals begins. The fluid samples of the reaction products are analysed by means of high pressure liquid chromatography (HPLC). The gas output from the gas - fluid separator is measured and analysed by means of gas chromatography in order to ascertain the presence of any hydrocarbons (methane, ethane etc) and carbon dioxide. The fluid product contains mainly 1,2-propylene glycol, ethanediol, butanediol and a smaller amount of glycerol, lactic acid and monovalent alcohols, as well as products such as erythritol and pentanediol. The gas output from the reactor contains hydrogen and traces of carbon dioxide. The results of examples 12 - 14 for two different reaction temperatures and two different LHSV values are contained in tables 7 and 8 hereinafter, relative respectively to the operative conditions and distribution of the reaction products.

TABLE 7

Example	Total pressure (kPa)	Temp. (°C)	S = supply (ppm)	Sorbitol/NaOH (molar ratio)	H ₂ /Sorb. (molar ratio)	LHSV (h ⁻¹)	Conversion (% sorbitol)
12	15	250	0	3	9	1	97
13	15	225	0	3	9	1	96
14	15	225	0	3	9	0.667	99.4

TABLE 8

Example	methane	monovalent alcohols	ethanediol	1-2 propylene glycol	butanediol	glycerol	lactic acid	others
12	2	5.6	18	43	15	5.8	4.4	6.2
13	0.4	2.8	18.5	48	12.8	7.5	3.3	6.7
14	0.2	2.6	18.3	47.3	13.3	5.6	3.6	9.1

CLAIMS

1. A metallic catalyst composition on an inert support, suitable in particular for hydrogenolysis reactions of higher polyhydric alcohols, characterised in that it comprises the following relative to 100 parts of the catalyst:

- a) 0.5 to 5 weight % ruthenium;
 - b) 1 to 10 weight % of a metal selected from the group consisting of palladium, platinum and rhodium; and
 - c) 0.5 to 2.5 weight % copper,
- in which the copper content is lower than the content of the metal b).

2. A catalyst composition according to Claim 1, characterised in that it comprises:

- a') 1 to 3 weight % ruthenium;
- b') 2 to 6 weight % palladium; and
- c') 0.5 to 2 weight % copper,

3. A catalyst composition according to either of Claims 1 or 2, in which the inert support is activated carbon.

4. A catalyst composition according to Claim 3, in which the metals are supported on granulated carbon, and in which this composition has:

- a specific surface area of 600 to 1000 m²/g;
- a total pore volume of 0.5 to 1.2 cm³/g:

- an apparent specific weight (bulk density) of 0.45 to 0.55 g/cm³;
- an actual specific weight of 1.9 to 2.3 g/cm³;
- a total volume of micropores having a radius smaller than 75 Å of 0.4 to 0.55 cm³/g; and
- an ash content of 2 to 5 weight %

5. A catalyst composition according to Claim 4, in which the weight ratio of palladium / copper is between 2 and 4.

6. A method for preparing a catalyst according to Claim 3, in particular for hydrogenolysis reactions of higher polyhydric alcohols, characterised in that it comprises the operations of:

- I) preparing an aqueous solution comprising a compound of ruthenium and a second metal selected from the group consisting of palladium, platinum and rhodium;
- II) putting this aqueous solution into contact with an aqueous suspension of an activated carbon, and regulating the pH by adding an alkaline agent until a value of between 4.5 and 8 is obtained;
- III) heating to a temperature of 60 to 100°C for a time sufficient to give rise to depositing of compounds of the metals on the activated carbon, and separation of this solid;
- IV) suspending the solid thus obtained in an alkaline solution and hydrogenating the suspension thus obtained

with gaseous hydrogen at a temperature of between 60° and 100°C for a time sufficient to give rise to production of the metals deposited on the support; and V) adding to the suspension an aqueous solution including copper at a temperature lower than 50°C and maintaining the suspension at this temperature, under agitation, for a time sufficient to give rise to depositing of the copper, and recovery of the solid support;

the concentration of the metals in the solution I) and V) being such as to obtain a catalyst comprising:

- a) 0.5 to 5 weight % ruthenium;
- b) 1 to 10 weight % of a metal selected from the group consisting of palladium, platinum and rhodium; and
- c) 0.5 to 2.5 weight % copper, the copper concentration being lower than the content of the metal b).

7. A method according to Claim 6 in which the activated carbon is in granulated form with:

- a specific surface area of 600 to 1000 m²/g;
- a total pore volume of 0.5 to 1.2 cm³/g;
- an apparent specific weight (bulk density) of 0.45 to 0.55 g/cm³;
- an actual specific weight of 1.9 to 2.3 g/cm³;
- a total volume of micropores having a radius smaller than 75 Å of 0.4 to 0.55 cm³/g; and
- an ash content of 3 to 5 weight %

8. A method according to Claim 7, in which the aqueous solution in I) is prepared by dissolving in water ruthenium trichloride and a palladium compound selected from amongst H_2PdCl_4 and Na_2PdCl_4 .

9. A method according to Claim 7, in which the aqueous solution including copper in V) is prepared by dissolving copper formate in water.

10. A method for producing lower polyhydric alcohols and their mixtures by means of hydrogenolysis under pressure of higher polyhydric alcohols, in the presence of a supported metal catalyst, characterised in that a catalyst according to Claim 3 is used.

11. A method according to Claim 10, characterised in that the reaction temperature is between 220° and $270^\circ C$.

12. A method according to Claim 10, characterised in that the hydrogenolysis reaction is carried out continuously in a fixed bed, in which the higher polyhydric alcohols or their mixtures are supplied in an aqueous solution with a concentration of 20 to 40 weight % at a spatial velocity of the supply of between 0.3 and $4\ h^{-1}$, and preferably between 0.66 and $2.50\ h^{-1}$.

13. A method according to Claim 10, in which the reaction pressure is between 7.5 and 20 MPa.

14. A method according to Claim 10, characterised in that the supply comprises an alkaline or alkaline earth metal hydroxide as a reaction promoter, and the molar ratio between the higher polyhydric alcohols and alkaline or alkaline earth hydroxide is between 3 and 30.

15. A method according to Claim 10, in which the higher polyhydric alcohol or mixture of higher polyhydric alcohols is the product obtained in a first stage of hydrogenation of carbohydrates carried out at a low basic pH.

16. A method according to Claim 15, in which the pH in the first stage of hydrogenation is adjusted to between 7.5 and 8 by addition of an alkaline or alkaline earth hydroxide.

17. A method according to Claim 16, in which the hydrogenation stage is carried out in a fixed bed reactor using a catalyst comprising between 0.5 and 5 weight % ruthenium supported on activated granulated carbon which has:

- a specific surface area of 600 to 1000 m²/g;

- a total pore volume of 0.5 to 1.2 cm³/g;
- an actual specific weight of 1.9 to 2.3 g/cm³;
- a total volume of micropores having a radius smaller than 75 Å of 0.4 to 0.55 cm³/g; and
- an ash content of 2 to 5 weight %.

INTERNATIONAL SEARCH REPORT

PCT/EP 93/00194

International Application No

I. CLASSIFICATION OF SUBJECT MATTER (if several classification symbols apply, indicate all) ⁶		
According to International Patent Classification (IPC) or to both National Classification and IPC		
Int.Cl. 5 B01J23/89; B01J23/46; B01J21/18; C07C29/00		
II. FIELDS SEARCHED		
Minimum Documentation Searched ⁷		
Classification System	Classification Symbols	
Int.Cl. 5	B01J ; C07C	
Documentation Searched other than Minimum Documentation to the Extent that such Documents are Included in the Fields Searched ⁸		
III. DOCUMENTS CONSIDERED TO BE RELEVANT⁹		
Category ^o	Citation of Document, ¹¹ with indication, where appropriate, of the relevant passages ¹²	Relevant to Claim No. ¹³
X	US,A,3 901 827 (J. H. SINFELT) 26 August 1975 see example 4	1,2
Y	---	3-8, 10-17
A	FR,A,2 223 337 (INSTITUT FRANCAIS DU PETROLE) 25 October 1974	
Y	US,A,4 430 253 (M. DUBECK) 7 February 1984 see claims 1-5; examples 1,2,10-12	3,5,6,8, 10-16
Y	EP,A,0 191 373 (AMERICAN CYANAMID COMPANY) 20 August 1986 see claims 1,2 see page 3, line 17 - line 22	4,7,17
<p>^o Special categories of cited documents : ¹⁰</p> <p>"A" document defining the general state of the art which is not considered to be of particular relevance</p> <p>"E" earlier document but published on or after the international filing date</p> <p>"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)</p> <p>"O" document referring to an oral disclosure, use, exhibition or other means</p> <p>"P" document published prior to the international filing date but later than the priority date claimed</p> <p>"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention</p> <p>"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step</p> <p>"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.</p> <p>"&" document member of the same patent family</p>		
IV. CERTIFICATION		
Date of the Actual Completion of the International Search		Date of Mailing of this International Search Report
02 JUNE 1993		18.06.93
International Searching Authority		Signature of Authorized Officer
EUROPEAN PATENT OFFICE		THION M.A.

**ANNEX TO THE INTERNATIONAL SEARCH REPORT
ON INTERNATIONAL PATENT APPLICATION NO.**

EP 9300194
SA 69424

This annex lists the patent family members relating to the patent documents cited in the above-mentioned international search report.
The members are as contained in the European Patent Office EDP file on
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

02/06/93

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US-A-3901827	26-08-75	None	
FR-A-2223337	25-10-74	BE-A- 811865	05-09-74
		CA-A- 1027974	14-03-78
		DE-A, C 2414282	17-10-74
		JP-C- 1128736	24-12-82
		JP-A- 50024227	15-03-75
		JP-B- 57015731	01-04-82
		NL-A- 7404095	30-09-74
		US-A- 4201661	06-05-80
US-A-4430253	07-02-84	US-A- 4476331	09-10-84
EP-A-0191373	20-08-86	US-A- 4591578	27-05-86
		CA-A- 1263105	21-11-89
		JP-A- 61222538	03-10-86
		US-A- 4687784	18-08-87